

KUTWELL

KUTWELL
KUTWELL

Soluble Cutting Oil

Product Description

KUTWELL is the trademark for a line of two high-performance 'soluble' cutting fluids for cooling and lubricating the tool and work in machining operations. The line includes one petroleum-base fluid, KUTWELL 40, and one semi-synthetic fluid, KUTWELL 82.

KUTWELL products mix readily into water to form stable emulsions. They have excellent rust-preventive properties, both are inhibited

wide

against foaming, and both are versatile products suitable for a

a

range of metal cutting and grinding operations. KUTWELL products effectively remove heat from the work piece and can be applied as

stream or in mist form.

minimal

In many cases, the proper KUTWELL grade can replace straight

cutting oils, and a single grade may often serve all the machine tools in a plant.

Features & Benefits

grade,

Available in one petroleum-base grade and one semi-synthetic

they offer the following features and advantages:

- Excellent emulsion stability
- Excellent rust protection
- Outstanding lubricating properties
- Dependable cooling of tool and work

Applications

KUTWELL water-mix cutting and grinding fluids are suitable for a wide range of ferrous and non-ferrous metalworking operations.

KUTWELL 40 is a premium quality soluble oil offering outstanding emulsion stability and rust inhibition. It emulsifies easily and resists oil-water separation in adverse operating conditions, such

66-82

as poor water quality or contamination with dirt or tramp oil. KUTWELL 40 also contains a bactericide to help guard against the formation of objectionable odors. Diluted as a 95:5 water-oil mixture, it can also be used as a fire-resistant hydraulic oil. Additionally, manufactured parts can be cleaned and protected against rusting by immersing them in a KUTWELL 40 emulsion at

°C, then allowing the parts to dry.

operations.

KUTWELL 82 is a water-soluble, biostable semi-synthetic product particularly recommended for light-to-moderate machining

It mixes easily with water, with little or no agitation, forming a translucent blue cutting fluid. The inherent lubricity of its



KUTWELL

chemical base assures effective lubrication under moderate-duty cutting or grinding of cast iron, steel, copper and most aluminum alloys.

In most applications, KUTWELL 82 lubricates more effectively at higher water dilution ratios than conventional soluble oils. This provides superior cooling performance and, in some machining operations, higher production rates.

The excellent rust-preventive properties of KUTWELL 82 derive from the combined effect of two additives. One provides a protective film that physically coats the metal surface. The other, a polar material, forms a supplemental film that preferentially attaches to the metal surface.

KUTWELL 82 is safe, clean, and pleasant to use. It exhibits excellent chemical and physical stability in service. It has inherent resistance to rancidity and inhibits the growth of mold and bacteria. It does not have an oily feel when spilled on surrounding surfaces.

For grinding, dilution ratios range from 30:1 to 80:1, with 50:1 a fair average for all ferrous materials. Dilutions for typical cutting operations range from 10:1 to 40:1 -- averaging about 25:1. Stronger concentrations are required for difficult operations, e.g., 5:1 to 15:1 for threading stainless steel.

Note : Because KUTWELL 82, as delivered, contains water, it is necessary to keep the product from freezing.

Preparation of Soluble Oils

Soluble oils are prepared for use by mixing them with relatively large portions of water. Note: To achieve a stable emulsion, always add oil to water - never add water to oil. For best emulsion stability and protection against rust and bacterial growth, use deionized or low hardness water (<100ppm). Begin by stirring one part oil into four parts water. Next, add water to this mixture to reach the desired dilution. The oil-water ratio may change during operation due to water evaporation and the filter's removal of oil attached to fine particles. Thus, it is important to regularly sample the oil concentration. This can be done by drawing off a representative sample in a graduated glass cylinder and breaking the emulsion with a saturated salt solution, such as Epsom salts. The oil concentration can easily be observed. Alternatively, the emulsion strength can be estimated by means of hand-held refractometers. Avoid storing soluble oils below freezing temperatures. If freezing should occur, re-warm the emulsion to room temperature and mix well before using.

Typical Properties



KUTWELL

KUTWELL

40

82

Color, ASTM 2.0 (Clear Blue)

Density @ 15°C (kg/L) 0.891.00

Emulsion Stability Excellent Good

Pour Point, °C -6 32 (Freezing)

Viscosity, cSt @ 40 °C 35 39

Health & Safety

Care should be taken to prevent metalworking fluids from coming in contact with the skin or splashing into the eyes. Oils and greases in contact with skin can result in plugging of sweat glands and

hair

follicles. In the castoff soluble oil, some defatting of the skin may occur. These conditions may lead to skin irritation or dermatitis. Accordingly, good personal hygiene should always be practiced. Oils, greases, and other foreign materials should

always

be removed from the skin promptly. Where repeated skin contact occurs, protective skin creams, such as silicone-base creams, applied to clean hands prior to contact may be beneficial. KUTWELL

cleaners

fluids are readily removed from the skin by waterless hand cleaners followed by washing with soap, water, and a soft skin brush.

KUTWELL

Soiled clothing should not remain in contact with the skin.

fluids can be removed from clothing by dry-cleaning or by washing with laundry detergents. Neat (unemulsified) metalworking oils, especially those containing high concentrations of emulsifiers or rust inhibitors, present a potential hazard to the eyes if allowed

slight

to enter and remain in contact with the eyes. When diluted to water-oil ratios of 20:1 or greater, however, the effects are

safety

and transient. As a precaution when handling KUTWELL fluids,

the

glasses, a face shield, or similar protection should be worn and normal safety practices followed. If the fluid is splashed into

eyes

eyes, immediately flush the eyes for 15 minutes with water. The

because

should be protected in any case during machining operations, the fluid in use is normally contaminated with fine metal chips or abrasive particles.

KUTWELL products do not contain nitrosamines, phenols or nitrates.

However, KUTWELL 82 contains an amine-type emulsifying agent.

and

WARNING: "Empty" containers retain residue (liquid and/or vapor)

drill,

can be dangerous. Do not pressurize, cut weld, braze, solder,

Do

grind, or expose such containers to heat, flame, sparks, or other sources of ignition; they may explode and cause injury or death.



KUTWELL

even

not attempt to clean since residue is difficult to remove, and a trace of remaining material constitutes an explosive hazard. "Empty" drums should be completely drained, properly bunged, and promptly returned to a drum reconditioner. All other containers should be disposed of in an environmentally safe manner and in accordance with governmental regulations.

Additional important health and safety information on this product can be found in the Material Safety Data Sheet which is available online at www.exxon.com or by contacting Exxon Branded Lubricants,

America

ExxonMobil Lubricants & Petroleum Specialties Company, North Technical Services - MSDS, 3225 Gallows Road, Fairfax, VA 22037.

03-2003

Exxon Mobil Corporation
3225 Gallows Road
Fairfax, VA 22037
1-800-44Exxon (443-9966)

on

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly. This product data sheet is based on global product data sheets for use with products purchased in the U.S.
© 2001 Exxon Mobil Corporation. All rights reserved.

